

#10-16 Flex5 SD3

Selectively hardened with Grade 5 performance





Features and Benefits

- Made from alloy steel and finished with a selective hardness heat treatment process to give the load bearing part of the fastener Grade 5 specifications (RC 28-34), with a higher hardness for the drill point and lead-in threads (min. RC52).
- Increased fastener ductility helps prevent hydrogen embrittlement
- Designed to have low driving and thread engagement torque and provide maximum clamp load
- VistaCorr[™] proprietary coating provides improved appearance, 1000 hour corrosion resistance, durability and installation performance

- **Application**
- Metal panel to light and medium gauge metal application
- Curtain wall
- · Rainscreen and cladding
- Fenstration systems
- Solar panel systems connecting aluminum to steel
- Dissimilar metal applications when used with aluminum

Approvals

• Listed on Intertek CCRR-0347 report



Product Selection


Material No.	Fastener Length		Load Bearing Area		Description	Carton Wt. (lbs.)	Carton Qtv.
	(in)	(mm)	(in)	(mm)	Description	Carton vvt. (ibs.)	Carton Qty.
1429720	3/4"	19	0.380"	9.7	FS3-#10x3/4-HW5/16-BQ	40	5,000

Product bulk carton packed.



#10-16 Flex5 SD3

Selectively hardened with Grade 5 performance



Product Specifications

Diameter: #10 (4.7 mm)

Threads Per Inch: 16

Head Style: 5/16" dia. HWH AF (7.8 mm)

Material: Selectively hardened alloy steel with

Grade 5 performance

Drill Point: SD3

Drill Capacity: 0.036"-0.150" (0.91 mm-3.81 mm)

Thread Major Dia: 0.186" (4.7 mm) Thread Minor Dia: 0.138" (3.5 mm)

Performance Data^{1,2,3}

Ultimate Material Strength

1938 lbf / 8621 N		
1358 lbf / 6041 N		
61 lbf·in / 6.89 N·m		

Ultimate Pull Out Strength Steel

20 Ga (0.9 mm)	306 lbf / 1361 N
18 Ga (1.2 mm)	447 lbf / 1988 N
16 Ga (1.5 mm)	523 lbf / 2326 N
14 Ga (1.9 mm)	821 lbf / 3652 N
10 Ga (3.5 mm)	1724 lbf / 7669 N

Installation and Application Considerations

Tools: 0–2000 rpm screw gun equipped with depth sensing nose piece.

Fasteners should provide for a minimum of 3/16" penetration of fully developed threads into the metal substrate.

Use of impact guns or hammer drills is not recommended.

¹ CCRR-0347

² See CCRR-0347 for allowable loads

³ PLK 19616