

#12-14 Flex5 SD3

Selectively hardened with Grade 5 performance



Features and Benefits

- Made from alloy steel and finished with a selective hardness heat treatment process to give the load bearing part of the fastener Grade 5 specifications (RC 28-34), with a higher hardness for the drill point and lead-in threads (min. RC52).
- Increased fastener ductility helps prevent hydrogen embrittlement
- Designed to have low driving and thread engagement torque and provide maximum clamp load
- VistaCorrTM proprietary coating provides improved appearance, 1000 hour corrosion resistance, durability and installation performance

Application

- Metal panel to light and medium gauge metal application
- Curtain wall
- Rainscreen and cladding
- Fenstration systems
- Solar panel systems connecting aluminum to steel
- Dissimilar metal applications when used with aluminum

Approvals

• Listed on Intertek CCRR-0347 report



Product Selection

| Material No. | Fastener Length | | Load Bearing Area | | Description | Conton M(t. (lbs.) | Conton Otro |
|--------------|-----------------|------|-------------------|------|-------------------------|--------------------|-------------|
| | (in) | (mm) | (in) | (mm) | Description | Carton Wt. (lbs.) | Carton Qty. |
| 1429731 | 7/8" | 22 | 0.380" | 9.7 | FS3-#12x7/8-HW5/16-BQ | 44 | 4,000 |
| 1429732 | 1" | 25 | 0.500" | 12.7 | FS3-#12x1-HW5/16-BQ | 44 | 4,000 |
| 1429734 | 1-1/2" | 38 | 1.000" | 25.4 | FS3-#12x1-1/2-HW5/16-BQ | 38 | 2,500 |
| 1429736 | 2" | 51 | 1.500" | 38.1 | FS3-#12x2-HW5/16-BQ | 16 | 2,000 |


Product bulk carton packed.

US T 800 234 4533 us.sfs.com Canada T 866 847 5400 ca.sfs.com Metric values are approximate conversions.

All information is non-binding and without guarantee. Before using the products, all specifications and calculations must be checked by a suitably qualified person and local regulations must be observed. This document is subject to revision. We reserve the right to make technical changes. (03/2021, V1.02)



#12-14 Flex5 SD3 Selectively hardened with Grade 5 performance



Performance Data^{1,2,3}

| Ultimate M | laterial Strength | Ultimate Pull Out Strength Steel | | |
|------------|---------------------------------------|----------------------------------|-------------------|--|
| Tensile | 3310 lbf / 14724 N | 20 Ga (0.9 mm) | 301 lbf / 1339 N | |
| Shear | 2041 lbf / 9079 N | 18 Ga (1.2 mm) | 439 lbf / 1953 N | |
| Torsional | 92 lbf·in / 10.4 N·m | 16 Ga (1.5 mm) | 532 lbf / 2366 N | |
| | · · · · · · · · · · · · · · · · · · · | 12 Ga (2.7 mm) | 1340 lbf / 5961 N | |
| | | 3/16" (4.8 mm) | Exceeds tensile | |

¹ CCRR-0347

US

T 800 234 4533

us.sfs.com

² See CCRR-0347 for allowable loads ³ PLK 17815

Installation and Application Considerations

Tools: 0–2000 rpm screw gun equipped with depth sensing nose piece.

Fasteners should provide for a minimum of 3/16" penetration of fully developed threads into the metal substrate.

Use of impact guns or hammer drills is not recommended.

T 866 847 5400 ca.sfs.com

Canada

Metric values are approximate conversions.

All information is non-binding and without guarantee. Before using the products, all specifications and calculations must be checked by a suitably qualified person and local regulations must be observed. This document is subject to revision. We reserve the right to make technical changes. (03/2021, V1.02)